



# Resudeck

Revised 05/2018 Issue 1—REF : DEST 2016

## DESCRIPTION

Resudeck is a two-pack, high build, hard wearing polyurethane floor coating providing a tough flexible finish with resistance to chemical attack. Resudeck is suitable for wet environments and is resistant to hot water. By incorporating suitable aggregates, anti-slip finishes can be created with a range of thicknesses and textures.

## ADVANTAGES

- Low odour
- Solvent free
- Flexible
- Can be applied onto concrete, wood and asphalt etc
- Excellent slip resistance with the use of selected aggregates
- Excellent resistance to most fuels and lubricants
- Very low VOC content

## RECOMMENDED USES

- Mezzanine areas
- Food units
- Bakeries
- Basement car parks
- Plant rooms
- Vehicle decks
- Asphalt areas

## PRODUCT INFORMATION

<b>System Thickness (Recommended)</b>	200-500 microns DFT
<b>Solids Content by Weight</b>	100% solids by weight
<b>Pack Sizes</b>	5 litres
<b>Pack Make Up</b>	1 x Base 1 x Hardener
<b>Shelf Life</b>	36 months (Base) & 12 months (Hardener)
<b>Storage</b>	Keep out of direct sunlight. Store in a dry place, between 15°C- 30°C.

## APPLICATION INFORMATION at 20°C

<b>Coverage Rate (Theoretical)</b>	5 litres will cover 25m <sup>2</sup> @ 200 microns wet film thickness. *Coverage rate is calculated based on a sealed and smooth surface and may vary based on the substrate roughness and other conditions.
<b>Pot Life</b>	20 Minutes
<b>Recoating Intervals</b>	6-8 hours
<b>Light Traffic</b>	6-8 hours
<b>Full Traffic</b>	24-48 hours
<b>Full Chemical Cure</b>	7 Days



## Specification

**Product :** Resudeck

**Finish :** Gloss

**Recommended thickness range:** 200 to 500 microns DFT per coat

**Colour :** Available in a range of colours, please consult Sherwin-Williams

## Products required for this system

**Primer :** Resuseal WB, Resuprime NT, R.S. Dampshield FH on damp surfaces or Resuprime ZP on metal/steel substrates.

**System :** Resudeck

**Surface Seal :** Not required

## Preparation

**New Concrete Floors:** New concrete must be clean, sound, dry, fully cured and surface laitance removed by vacuum enclosed shot blasting or mechanical grinding, a minimum strength of 25N/mm<sup>2</sup> is required.

**Existing Concrete Floors:** Remove all dirt, oil, grease, old paint or any other surface contaminants by vacuum enclosed shot blasting, scarifying or mechanical grinding. Fats, oils or greases must be removed by mechanical means and detergent washing and make sure all residue of detergent is washed and removed by rinsing with clean water. Local repairs should be carried out using **Resupatch** or **Resuscreed 45**.

### Existing Floors ( previously coated )

All previous coatings and loose floor paints must be removed by mechanical preparation as described in the above section and primed as specified. If the old resin flooring cannot be removed, then please consult with our technical team for advice on intercoat adhesion and suitability, as it may not be compatible with existing floor coating.

Where **Resudeck** is applied to masonry/concrete surfaces, care must be taken to ensure that surface preparation is thorough but does not disfigure the surface.

## Priming

Open and porous substrates may require priming with **Resuseal WB**, also **Resuprime NT** may be used as primer on the dry substrates only with less than 75% ERH reading. **Resuprime ZP** should be used as a primer onto steel substrates where appropriate.

Where the Relative Humidity of a substrate exceeds 75% ERH **R.S. Dampshield FH** should be specified and selected on the basis of hygrometer readings in accordance with BS 8203. The number of coats to be applied is chosen in accordance with the following table.

ERH%	Required Coating Thickness
75-85	1 coat of R.S.DAMPSHIELD FH at 200 microns per coat
85-92	2 coats of R.S.DAMPSHIELD FH at 200 microns per coat
92-97	3 coats of R.S.DAMPSHIELD FH at 200 microns per coat

For Further information please refer to recommended individual product data sheets.

## Application

The ambient temperatures of the areas should not be allowed to fall below 15°C throughout the application and the curing period, as this could have an adverse effect on the appearance and colour of the system. Surface temperature must be above 5°C. Where possible it is recommended that the application area is heated to a minimum temperature of 15°C ideally to allow the ambient and substrate temperature to stabilise prior to installation.

Pre-mix the coloured base component to a uniform consistency then mix the entire contents of the base with the hardener. If a separate mixing bucket is being used mix thoroughly ensuring all contents of both components are removed from the buckets supplied. Mix using a slow speed electric mixer for approximately two to three minutes until the two components have fully combined.

The mixed unit should be applied immediately by squeegee, roller or brush with a consistent procedure. Floor areas should be cross-rolled to ensure even application and to minimise roller marks. Coverage rates may vary depending on profile and porosity of the substrate.

**NOTE: Resudeck** is not UV stable and will yellow with time. This is a surface discolouration under the effect of UV light and does not affect the durability of the floor finish. Darker colours will not show this effect as much as light colours.

## Category Guide

FeRFA Category : 3

## Technical Information

The following figures are obtained from laboratory tests and our experience with this product .

Slip Resistance	Dry > 60
Method BS7976 pt1-3 2002	Wet Please consult Sherwin-Williams

The slip resistance of a floor surface can vary as a result of the installation process, conditions at the time of application and subsequent traffic. Inappropriate cleaning or maintenance can adversely affect the performance. For further advice on potential wet areas please consult Sherwin-Williams.

Abrasion Resistance	AR 0.5
Method BS EN 13892-4	(Less than 50µ wear)

Temperature Resistance	Tolerant of temperatures up to 70°C
------------------------	-------------------------------------

Chemical Resistance	Very Good Chemical Resistance
	Consult Sherwin-Williams on specific materials

VOC	<1 g/l Calculated per full mixed unit
-----	---------------------------------------

Life Expectancy	Up to 4 years depending on applied thickness and subjected to traffic according to FeRFA classification. Sherwin-Williams terms and conditions will apply.
-----------------	------------------------------------------------------------------------------------------------------------------------------------------------------------

## Maintenance and Cleaning

**Resudeck** should be cleaned with a regular industrial cleaning regime, after specified full chemical cure time limit, with a floor scrubber utilising **R.S. Industrial Floor Cleaner** or similar with dirty water being removed. Isolated localised cleaning can be carried out using **R.S. Tyre Mark Remover**, **R.S. Fats, Oils & Grease Remover** & **R.S. Oil Remover**.

All surfaces should be thoroughly rinsed with clean water after the use of chemical cleaners.

## Health and Safety

**Resudeck** is formulated from materials designed to achieve the highest level of performance as safely as possible. However, specific components require proper handling and suitable equipment, this information is given in the relevant safety data sheets. In all cases, spillages or skin contamination should be cleaned as soon as practically possible, by dry wiping of the affected area, and thorough washing with soap and water.

The information given in this data sheet is derived from tests and experience with the products and is believed to be reliable. The information is offered without guarantee to enable purchasers to determine for themselves the suitability of the product for their particular application. Any specification or advice given by the Sherwin-Williams or its agents is based on the information supplied by the purchaser. Sherwin-Williams cannot be held accountable for errors or omissions as a result of that information being incorrect or incomplete. No undertakings can be given against infringement of patents. Some materials are derived from natural sources. As such some variation may occur. Site conditions may also contribute to variation in finish and colour.

Sherwin-Williams Protective & Marine  
Tower Works, Kestor Street, Bolton, BL2 2AL, United Kingdom,  
Tel : + 44 (0) 1204 521771 F: + 44 (0) 1204 382115  
W : Sherwin-williams.com/protectiveEMEA1  
Registered in England : Reg. No. 893081  
Reg. Office Tower Works, Kestor Street, Bolton BL2 2AL England