



Resugrip

Revised 05/2018 Issue 1—REF : GPST

DESCRIPTION

Resugrip is a 3 component, solvent-free un-pigmented polyurethane binder for surface dressing with aggregates to create non-slip textured floor finishes. Resugrip systems can be used in interior or exterior situations on a variety of substrates to provide high wear resistant anti-slip finishes. Resugrip, whilst not UV stable, can be top coated with UV stable coatings where required.

ADVANTAGES

- Excellent slip resistant finish
- Extremely hard wearing
- Can be decorative through the use of coloured aggregates
- High bond strength
- Will cure at temperatures down to 5°C

RECOMMENDED USES

- Theme parks
- Public pathways
- Public concourse areas
- Loading bays
- Walkways around buildings and factories
- Demarcation of non-slip areas

PRODUCT INFORMATION

System Thickness (Recommended)	1.5-2mm
Solids Content by Weight	100% solids by weight
Pack Sizes	29 Kg
Pack Make Up	1 x Base 1 x Hardener 1 x Aggregate
Shelf Life	12 months (Base, Hardener & Aggregate)
Storage	Keep out of direct sunlight. Store in a dry place, between 15°C- 30°C.

APPLICATION INFORMATION at 20°C

Coverage Rate (Theoretical)	29 Kg will cover 9.6m ² at 1.5mm thickness or 7.2m ² at 2mm thickness *Coverage rate is calculated based on a sealed and smooth surface and may vary based on the substrate roughness and other conditions.
Pot Life	10-15 Minutes
Recoating Intervals	6-8 hours
Light Traffic	6-8 hours
Full Traffic	16-24 hours
Full Chemical Cure	7 Days



Specification

Product : Resugrip

Finish : Textured finish with broadcasted aggregate

Recommended thickness range: 1.5-2mm

Colour : Natural

Products required for this system

Primer : Resuprime NT or R.S. Dampshield on damp surfaces, where required.

System : Resugrip

Optional Finish Coat: Resutop (Clear or coloured) or Resudeck. Resutile or Resupen WB where a UV stable coating is required.

Preparation

New Concrete Floors: New concrete must be clean, sound, dry, fully cured and surface laitance removed by vacuum enclosed shot blasting or mechanical grinding, a minimum strength of 25N/mm² is required.

Existing Concrete Floors: Remove all dirt, oil, grease, old paint or any other surface contaminants by vacuum enclosed shot blasting, scarifying or mechanical grinding. Fats, oils or greases must be removed by mechanical means and detergent washing and make sure all residue of detergent is washed and removed by rinsing with clean water. Local repairs should be carried out using Resupatch.

Existing Floors (previously coated)

All previous coatings and loose floor paints must be removed by mechanical preparation as described in the above section and primed as specified. If the old resin flooring cannot be removed, then please consult with our technical team for advice on intercoat adhesion and suitability, as it may not be compatible with existing floor coating.

Priming

Open and porous substrates will require priming with **Resuprime NT** on dry substrates only with less than 75% ERH reading.

Where the Relative Humidity of a substrate exceeds 75% ERH **R.S. Dampshield** should be specified and selected on the basis of hygrometer readings in accordance with BS 8203. The number of coats to be applied is chosen in accordance with the following table.

ERH%	Required Coating Thickness
75-85	1 coat of R.S.DAMPSHIELD at 200 microns per coat
85-92	2 coats of R.S.DAMPSHIELD at 200 microns per coat
92-97	3 coats of R.S.DAMPSHIELD at 200 microns per coat

75-85	1 coat of R.S.DAMPSHIELD at 200 microns per coat
85-92	2 coats of R.S.DAMPSHIELD at 200 microns per coat
92-97	3 coats of R.S.DAMPSHIELD at 200 microns per coat

For further information please refer to individual product data sheets.

Application

The ambient temperatures of the areas should not be allowed to fall below 10°C throughout the application and the curing period, as this could have an adverse effect on the appearance and colour of the system. Surface temperature must be above 5°C. Where possible it is recommended that the application area is heated to a minimum temperature of 15°C ideally to allow the ambient and substrate temperature to stabilise prior to installation.

Pre-mix the base component to a uniform colour, then mix the entire contents of base with the hardener. If a separate mixing bucket is being used ensure all contents of both components are removed from the buckets supplied. Mix using a slow speed electric mixer for approximately one to two minutes until the two components have fully combined then add the aggregate slowly. Mix for a further 1-2 minutes until the aggregate has fully combined and there are no lumps. The mixed unit should be applied immediately with a trowel or float to achieve an even smooth finish. This is best achieved by the application of smooth even pressure with the compound poured over the correct coverage rate after fixing the stop ends to control the flow of the material.

Then roll the area with a spiked roller to achieve an even smooth surface and remove entrapped air. Do not re-roll the area later than 10-15 mins. The surface should then be dressed with the selected aggregate at a rate of approximately 1-2 Kg/m².

The surface should be protected from temperatures of less than 5°C and moisture in the early stages of cure. This could adversely affect the flow, levelling and surface finish of **Resugrip**.

Category Guide

FeRFA Category : 4

Technical Information

The following figures are obtained from laboratory tests and our experience with this product .

Slip Resistance Dry > 60
Method BS7976 pt1-3 2002 Wet Please consult Sherwin-Williams

The slip resistance of a floor surface can vary as a result of the installation process, conditions at the time of application and subsequent traffic. Inappropriate cleaning or maintenance can adversely affect the performance. For further advice on potential wet areas please consult Sherwin-Williams.

Abrasion Resistance AR 0.5
Method BS EN 13892-4 (Less than 50µ wear)

Temperature Resistance Tolerant of temperatures up to 65°C

Chemical Resistance Good Chemical Resistance
Consult Sherwin-Williams on specific materials

VOC <5 g/l Calculated per full mixed unit

Life Expectancy Up to 5 years depending on applied thickness and subjected to traffic according to FeRFA classification. Sherwin-Williams terms and conditions will apply.


Sherwin-Williams Protective & Marine Tower Works, Kestor Street, Bolton BL2 2AL, United Kingdom Tel: +44 (0) 1204 521771 F: +44 (0) 1204 382115
13
BSEN 13813 SR B 3.5 - AR 0.5 - IR>4 Resin coating/screed for use inside buildings as per data sheet Wear resistance: AR 0.5 Bond strength: B 3.5 Impact resistance: IR 9

Maintenance and Cleaning

Resugrip should be cleaned with a regular industrial cleaning regime, after specified full chemical cure time limit, with a floor scrubber utilising **R.S. Industrial Floor Cleaner** or similar with dirty water being removed. Isolated localised cleaning can be carried out using **R.S. Tyre Mark Remover, R.S. Fats, Oils & Grease Remover & R.S. Oil Remover**.

All surfaces should be thoroughly rinsed with clean water after the use of chemical cleaners.

Please refer to the **Sherwin-Williams Guide to Cleaning of Resin Floors**

Health and Safety

Resugrip is formulated from materials designed to achieve the highest level of performance as safely as possible. However, specific components require proper handling and suitable equipment, this information is given in the relevant safety data sheets. In all cases, spillages or skin contamination should be cleaned as soon as practically possible, by dry wiping of the affected area, and thorough washing with soap and water.

The information given in this data sheet is derived from tests and experience with the products and is believed to be reliable. The information is offered without guarantee to enable purchasers to determine for themselves the suitability of the product for their particular application. Any specification or advice given by the Sherwin-Williams or its agents is based on the information supplied by the purchaser. Sherwin-Williams cannot be held accountable for errors or omissions as a result of that information being incorrect or incomplete. No undertakings can be given against infringement of patents. Some materials are derived from natural sources. As such some variation may occur. Site conditions may also contribute to variation in finish and colour.

Sherwin-Williams Protective & Marine
Tower Works, Kestor Street, Bolton, BL2 2AL, United Kingdom,
Tel : + 44 (0) 1204 521771 F: + 44 (0) 1204 382115
W : Sherwin-williams.com/protectiveEMEA
Registered in England : Reg. No. 893081
Reg. Office Tower Works, Kestor Street, Bolton BL2 2AL England